

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 August 2002 (22.08.2002)

PCT

(10) International Publication Number
WO 02/064653 A2

- (51) International Patent Classification⁷: C08F 291/00, C08L 51/08, 51/00, C08G 61/08, C08L 65/00
- (74) Agent: TAYLOR, Jonathan, P.; Brinks Hofer Gilson & Lione, P.O. Box 10087, Chicago, IL 60610 (US).
- (21) International Application Number: PCT/US02/04163
- (22) International Filing Date: 12 February 2002 (12.02.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/782,609 13 February 2001 (13.02.2001) US
- (71) Applicant: BOARD OF TRUSTEES OF UNIVERSITY OF ILLINOIS [US/US]; 352 Henry Administration Building, 506 S. Wright, Urbana, IL 61801 (US).
- (72) Inventors: WHITE, Scott, R.; 2510 Southwood Drive, Champaign, IL 61821 (US). SOTTOS, Nancy, R.; 1410 Manchester Drive, Champaign, IL 61822 (US). GEUBELLE, Philippe, H.; 2102 Crossgate Court, Champaign, IL 61822 (US). MOORE, Jeffery, S.; 807 Vista Drive, Savoy, IL 61874 (US). SRIRAM, Suresh, R.; 508 E. Michigan Avenue, Apt. 15, Urbana, IL 61801 (US). KESSLER, Michael, R.; 1303 W. Beardley Avenue, Urbana, IL 61801 (US). BROWN, Eric, N.; 621 South Crescent Drive, Apartment 20, Champaign, IL 61821 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: MULTIFUNCTIONAL AUTONOMICALLY HEALING COMPOSITE MATERIAL

(57) Abstract: A composite material, contains a polymer, a polymerizer, a corresponding catalyst for the polymerizer, and a plurality of capsules. The polymerizer is in the capsules. The composite material is self-healing.

WO 02/064653 A2

-1-

MULTIFUNCTIONAL AUTONOMICALLY HEALING COMPOSITE MATERIAL

FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

5 The subject matter of this application may in part have been funded by the Air Force (AFOSR Grant no. F49620-00-1-0094/White). The government may have certain rights in this invention.

BACKGROUND

The present invention relates to self-healing composite materials.

10 Thermosetting polymers, used in a wide variety of applications ranging from microelectronics to composite airplane wings, are susceptible to damage in the form of cracking. Often these cracks form deep within the structure where detection is difficult and repair is virtually impossible. In fiber reinforced polymer composites, cracking in the form of fiber-matrix interfacial debonding, ply delamination, and simple matrix cracking leads to degradation. In 15 microelectronics, polymer encapsulates and polymer matrix composite printed circuit boards suffer from similar forms of damage, but in addition to mechanical failure, cracks cause electrical failure of the component. Microcracking induced by thermal and mechanical fatigue is a longstanding problem in polymer adhesives. Regardless of the application, once cracks 20 have formed within polymeric materials, the integrity of the structure is significantly compromised. Typically, previously reported methods of successful crack healing require some form of manual intervention.

A proposed method of self-healing is described in "Self-Healing Composites Using Embedded Microspheres" D. Jung et al. Composites and Functionally Graded Materials vol. MD-80, in Proceedings of the ASME 25 International Mechanical Engineering Conference and Exposition, 265-275 (1997). The proposed method uses polyoxymethyleneurea (PMU) microspheres to store a crack filling agent to be released into the crack and rebond the crack faces. The repair mechanism uses naturally occurring 30 functional sites in a polyester matrix network to trigger the repair action. Adding a reactive component to trigger the crack filler solidification was

-2-

specifically investigated in the case of embedded epoxide components and embedded amine groups, and it was found that the amine groups did not retain sufficient activity and was determined to be not feasible. The PMU microcapsules used contained an epoxide monomer.

5 **BRIEF SUMMARY**

In a first aspect, the present invention is a composite material, containing: a polymer, a polymerizer, a corresponding catalyst for the polymerizer, and a plurality of capsules. The polymerizer is in the capsules.

10 In a second aspect, the present invention is a composite material, containing: a polymer, a polymerizer, a corresponding activator for the polymerizer, and a first plurality of capsules. The polymerizer is in the capsules, and the corresponding activator is not a native activating moiety.

15 In a third aspect, the present invention is a method for making the above composites, including dispersing the capsules and the corresponding catalyst or activator into the polymer.

Definitions

20 A polymerizer is a composition that will form a polymer when it comes into contact with a corresponding activator for the polymerizer. Examples of polymerizers include monomers of polymers such as styrene, ethylene, (meth)acrylates, and dicyclopentadiene (DCPD); a monomer of a multi-monomer polymer system such as diols, diamines, and epoxide; and prepolymers such as partially polymerized monomers still capable of further polymerization.

25 An activator is anything that when contacted or mixed with a polymerizer will form a polymer. Examples of activators are catalysts, initiators, and native activating moieties. A corresponding activator for a polymerizer is an activator that when contacted or mixed with that specific polymerizer will form a polymer.

30 A catalyst is a compound or moiety that will cause a polymerizable composition to polymerize, and is not always consumed each time it causes

-3-

polymerization. This is in contrast to initiators and native activating moieties. Examples of catalysts include ring opening polymerization (ROMP) catalysts such as Grubbs catalyst. A corresponding catalyst for a polymerizer is a catalyst that when contacted or mixed with that specific polymerizer will form a polymer.

An initiator is a compound that will cause a polymerizable composition to polymerize, and is always consumed at the time it causes polymerization. Examples of initiators are peroxides (which will form a radical to cause polymerization of an unsaturated monomer); a monomer of a multi-monomer polymer system such as diols, diamines, and epoxide; and amines (which will form a polymer with an epoxide). A corresponding initiator for a polymerizer is an initiator that when contacted or mixed with that specific polymerizer will form a polymer.

A native activating moiety is a moiety of a polymer that when mixed or contacted with a polymerizer will form a polymer, and is always consumed at the time it causes polymerization. Examples of a native activating moiety is an amine moiety (which will form a polymer with an epoxide).

A compound is a molecule that contains at most 100 repeating units. This is in contrast to a polymer, which contains more than 100 repeating units.

A capsule is a hollow closed object having an aspect ratio of 1:1 to 1:10. The aspect ratio of an object is the ratio of the shortest axis to the longest axis; these axes need to be perpendicular. A capsule may have any shape that falls within this aspect ratio, such as a sphere, a toroid, or an irregular ameboid shape. The surface of a capsule may have any texture, for example rough or smooth.

BRIEF DESCRIPTION OF THE DRAWINGS

Various other objects, features and attendant advantages of the present invention will be more fully appreciated as the same becomes better understood from the following detailed description when considered in connection with the accompanying drawings in which like reference

-4-

characters designate like or corresponding parts throughout the several views and wherein:

Figure 1 illustrates an embodiment of a self-healing composite; and
Figure 2 shows crack healing efficiency of the composite materials.

5 DETAILED DESCRIPTION

Further investigations by the group that published "Self-Healing Composites Using Embedded Microspheres" found that the use of natural functionality was, in fact, not feasible. Approaches that had been previously eliminated were reconsidered, resulting in the discovery that systems that do
10 not use a corresponding native activating moiety will allow for a self-healing composite. Preferably, systems that use a catalyst added to the polymer are used. Not only can damage to the composite be repaired, but also in some cases the achieved healed strengths are greater than the strength of the original matrix material.

15 The present invention includes a composite material, containing capsules in a polymer. The capsules contain a polymerizer, and the composite material includes an activator that is not a corresponding native activating moiety. Preferably, the activator is a corresponding catalyst for the polymerizer. When a crack forms in the composite material, some of the
20 capsules are broken, and the polymerizer moves into the crack, coming into contact with the activator and forming a polymer. This repairs the crack.

The capsules contain a polymerizer. The polymerizer contains a polymerizable compound such as a monomer or prepolymer, and may optionally contain other ingredients, such as other monomers and/or
25 prepolymers, stabilizers, solvents, viscosity modifiers such as polymers, odorants, colorant and dyes, blowing agents, antioxidants, and co-catalysts. Preferably, the polymerizer is a liquid.

The polymer contains both capsules and a corresponding activator for the polymerizer. Preferably, the activator is a catalyst or an initiator.
30 Examples of polymerizable compounds are cyclic olefins, preferably containing 4-50 carbon atoms and optionally containing heteratoms, such as

DCPD, substituted DCPDs, norbornene, substituted norbornene, cyclooctadiene, and substituted cyclooctadiene. Corresponding catalysts for these are ring opening metathesis polymerization (ROMP) catalysts such as Schrock catalysts (Bazan, G.C.; Schrock, R.R.; Cho, H.-N.; Gibson, V.C. *Macromolecules* **24**, 4495-4502 (1991)) and Grubbs catalysts (Grubbs, R.H.; Chang, S. *Tetrahedron* **54**, 4413-4450 (1998)).

Another example of polymerizable compounds are lactones such as caprolactone, and lactams, that when polymerized will form polyesters and nylons, respectively. Corresponding catalysts for these are cyclic ester polymerization catalysts and cyclic amide polymerization catalysts, such as scandium triflate.

Furthermore, a polymerizer may contain a polymerizable compound and one part of a two-part catalyst, with a corresponding initiator being the other part of the two-part catalyst. For example, the polymerizable compound may be a cyclic olefin; one part of a two-part catalyst may be a tungsten compound, such as an organoammonium tungstate, an organoarsonium tungstate, or an organophosphonium tungstate; or a molybdenum compound, such as organoammonium molybdate, an organoarsonium molybdate, or an organophosphonium molybdate. The second part of the two-part catalyst may be an alkyl aluminum compound, such as an alkoxyalkylaluminum halide, an aryloxyalkylaluminum halide, or a metaloxyalkylaluminum halide in which the metal in the compound is tin, lead, or aluminum; or an organic tin compound, such as a tetraalkyltin, a trialkyltin hydride, or a triaryltin hydride.

In another such system, the polymerizable compound may be unsaturated compounds such as acrylates; acrylic acids; alkyl acrylates; alkyl acrylic acids; styrenes; isoprene; and butadiene. In this case, atom transfer radical polymerization (ATRP) may be used, with one of the two components being mixed with the polymerizable compound and the other acting as the initiator: one component being an organohalide such as 1-chloro-1-phenylethane, and the other component could be a copper(I) source such as copper(I) bipyridyl complex. Alternatively, one component could be a peroxide such as benzoyl peroxide, and the other component could be a

nitroso precursor such as 2,2,6,6-tetramethylpiperidiny-1-oxy (TEMPO). These systems are described in Malcolm P. Stevens; *Polymer Chemistry: An Introduction*, 3rd Edition; New York: Oxford University Press, 1999, p. 184 - 186.

5 In another such system, the polymerizable compound may contain isocyanate functional groups ($-N=C=O$) with hydroxyl functional groups ($-OH$). For this system, the polymerizable material may for example be a compound containing both an isocyanate group and a hydroxyl group, or two different compounds, one compound containing at least two isocyanate groups and the
10 other compound containing at least two hydroxyl groups. The reaction between an isocyanate group and a hydroxyl group can form a urethane linkage ($-N-C(=O)-O-$) between the compounds, possibly releasing carbon dioxide. This carbon dioxide can provide for the creation of expanded polyurethane foam; optionally the polymerizer may contain a blowing agent,
15 for example a volatile liquid such as dichloromethane. In this case, condensation polymerization may be used, with one of the two components being mixed with the polymerizable compound and the other acting as the initiator: for example, one component could be an alkyltin compound such as stannous 2-ethylhexanoate, and the other component could be a tertiary
20 amine such as diazabicyclo[2.2.2]octane (DABCO). These systems are described in Malcolm P. Stevens; *Polymer Chemistry: An Introduction*, 3rd Edition; New York: Oxford University Press, 1999, p. 378 - 381.

 Optionally, the activator, such as the catalyst or initiator may also be in a separate set of capsules. Furthermore, this separate set of capsules may
25 also contain stabilizers, solvents, viscosity modifiers such as polymers, odorants, colorant and dyes, blowing agents, antioxidants, and co-catalysts. Optionally, a set of capsules may be present that contain one or more additional ingredients, such as stabilizers, solvents, viscosity modifiers such as polymers, odorants, colorant and dyes, blowing agents, antioxidants, and
30 co-catalysts.

 The capsules contain a polymerizer. Preferably, the capsules have an average diameter of 10 nm to 1 mm, more preferably 30-500 μ m, most

-7-

preferably to 50-300 μm . The capsules have an aspect ratio of 1:1 to 1:10, preferably 1:1 to 1:5, more preferably 1:1 to 1:3, and even more preferably 1:1 to 1:2, and most preferably 1:1 to 1:1.5.

5 The wall thickness of the capsules is preferably 100 nm to 3 μm . The selection of capsule walls thickness depends on the polymer in the composite. For example, capsule walls that are too thick will not rupture when a crack approaches, while capsules with very thin walls will break during processing.

10 The adhesion between the capsules and the polymer of the composite influences whether the capsules will rupture or debond in the presence of an approaching crack. To promote the adhesion between the polymer and capsule wall, various silane coupling agents may be used. Typically, these are compounds of the formula R-SiX_3 Where R is preferably a reactive group R^1 separated by a propylene group from silicon, and X is an alkoxy group (preferably methoxy), such as $\text{R}^1\text{CH}_2\text{CH}_2\text{CH}_2\text{Si}(\text{OCH}_3)_3$. Examples include
15 silane coupling agents available from DOW CORNING (with reactive group following the name in parentheses): Z6020 (Diamino); Z6030 (Methacrylate); Z6032 (Styrylamine Cationic); Z6040 (Epoxy); and Z6075 (Vinyl).

20 To increase the adhesion between the capsules and a polymer in the composite, the capsules may be treated by washing them in a solution of the coupling agent. For example, urea-formaldehyde capsules may be washed in a solution of Silane Z6020 or Z6040 and hexane (1:20 wt.) followed by adding Silane Z6032 to the polymer (1% wt.).

25 Capsules may be made by a variety of techniques, and from a variety of materials, such as those described in Microencapsulation: Methods and Industrial Applications Ed. Benita, Simon Marcel Dekker, New York, 1996; Microencapsulation: Processes and Applications Ed. Vandegaer, J. Plenum Press, New York, 1974; and Microcapsule Processing and Technology Kondo, A. Marcel Dekker, New York, 1979. Examples of materials from which the capsules may be made, and the techniques for making them include:
30 urea-formaldehyde, formed by *in situ* polymerization; gelatin, formed by complex coacervation; polyurea, formed by the reaction of isocyanates with a diamine or a triamine, depending on the degree of crosslinking desired (the

extent of crosslinking also determines the brittleness of the capsule); and polyamide, formed by the use of a suitable acid chloride and a water soluble triamine.

5 The polymer may be any polymeric material into which the capsules may be dispersed. Examples include polyamides such as nylons; polyesters such as poly(ethylene terephthalate) and polycaprolactone; polycarbonates; polyethers such as epoxides; polyimides such as polypyromellitimide (for example KAPTAN); phenol-formaldehyde resins (for example BAKELITE); amine-formaldehyde resins such as a melamine resin; polysulfones; 10 poly(acrylonitrile-butadiene-styrene) (ABS); polyurethanes; polyolefins such as polyethylene, polystyrene, polyacrylonitrile, polyvinyls, polyvinyl chloride, poly(DCPD) and poly(methyl methacrylate); polysilanes such as poly(carborane-siloxane); and polyphosphazenes.

15 The capsules and activator (such as the catalyst or initiator) may be dispersed into the polymer by forming the polymer around the capsules and activator, such as by polymerizing monomer to form the polymer with the capsules and activator mixed into the monomer. Particularly in the case of catalysts, the catalyst may serve as both a catalyst for the polymer and as the corresponding activator for the polymerizer in the capsules. Examples of this 20 system include DCPD as the polymerizer, the polymer is poly(DPCD), and a Grubbs catalyst serves to form the poly(DPCD) and acts as the activator for the DCPD in the capsules; and caprolactone as the polymerizer, the polymer is poly(caprolactone), and scandium triflate acts as the activator for the caprolactone in the capsules.

25 Alternatively, the polymer may be first formed, and then the capsules and activator mixed in. For example, the polymer may be dissolved in a solvent and the capsules and activator mixed into the solution, followed by removal of the solvent. The activator may be coated onto the capsules prior to dispersing the capsules into the polymer. Furthermore, other components 30 may be added to the polymer, such as fibers, fillers, adhesion modifiers, blowing agents, anti-oxidants, colorants and dyes, and fragrances.

Figure 1 illustrates an embodiment of a self-healing composite. An approaching crack ruptures embedded capsules (referred to as microcapsules in the figure) releasing polymerizer (referred to as healing agent in the figure) into the crack plane through capillary action. Polymerization of the healing agent may be triggered by contact with the activator (here a catalyst), bonding the crack faces. The damage-induced triggering mechanism provides site-specific autonomic control of the repair. As shown in Figure 1, an encapsulated healing agent is embedded in a structural composite matrix containing a catalyst capable of polymerizing the healing agent: (i) cracks form in the matrix wherever damage occurs, (ii) The crack ruptures the microcapsules, releasing the healing agent into the crack plane through capillary action, (iii) The healing agent contacts the catalyst triggering polymerization that bonds the crack faces closed.

EXAMPLES

The following examples and preparations are provided merely to further illustrate the invention. The scope of the invention is not construed as merely consisting of the following examples.

General Procedure for Preparation of Capsules by *In Situ* Polymerization

In a 600 mL beaker is dissolved urea (0.11 mol, 7.0 g) followed by resorcinol (0.5 g) and ammonium chloride (0.5 g) in water (150 ml). A 5 wt.% solution of ethylene maleic anhydride copolymer (100 mL) is added to the reaction mixture, and the pH of the reaction mixture is adjusted to 3.5 using 10 % NaOH solution. The reaction mixture is agitated at 454 rpm, and to the stirred solution is added 60 mL of dicyclopentadiene to achieve an average droplet size of 200 μ m. To the agitated emulsion is added 37% formaldehyde (0.23 mol, 18.91 g) solution, and then the temperature of the reaction mixture is raised to 50°C and maintained for 2 h. After 2 h, 200 mL of water is added to the reaction mixture. After 4 h, the reaction mixture is cooled to room temperature, and capsules are separated. The capsule slurry is diluted with an additional 200 mL of water and washed with water (3 x 500 mL). The

-10-

capsules are isolated by vacuum filtration, and air-dried. Yield: 80%.


Average size: 220 μm .

Composite Epoxy Specimen Manufacture

5 The epoxy matrix composite was prepared by mixing 100 parts EPON 828 (Shell Chemicals Inc.) epoxide with 12 parts DETA (diethylenetriamine) curing agent (Shell Chemicals Inc.). Composite epoxy specimens were prepared by mixing 2.5% (by wt.) Grubbs' catalyst and 10% (by wt.) capsules with the resin mixture described above. The resin was then poured into
10 silicone rubber molds and cured for 24 h at room temperature, followed by postcuring at 40 °C for 24 h.

Example

15 DCPD filled capsules (50-200 μm average diameter) with a urea-formaldehyde shell were prepared using standard microencapsulation techniques. The capsule shell provides a protective barrier between the catalyst and DCPD to prevent polymerization during the preparation of the composite.



The reaction scheme for the polymerization of DCPD is shown below

20

To assess the crack healing efficiency of these composite materials, fracture tests were performed using a tapered double-cantilever beam (TDCB) specimen (Fig 2). Self-healing composite and control samples were fabricated. Control samples consisted of: (1) neat epoxy containing no

-11-

Grubbs' catalyst or capsules, (2) epoxy with Grubbs' catalyst but no capsules and (3) epoxy with capsules but no catalyst. A sharp pre-crack was created in the tapered samples by gently tapping a razor blade into a molded starter notch. Load was applied in a direction perpendicular to the pre-crack (Mode I) with pin loading grips as shown in Fig. 2. The virgin fracture toughness was determined from the critical load to propagate the crack and fail the specimen. After failure, the load was removed and the crack allowed to heal at room temperature with no manual intervention. Fracture tests were repeated after 48 hours to quantify the amount of healing.

A representative load-displacement curve is plotted in Fig. 2 demonstrating ca. 75% recovery of the virgin fracture load. In great contrast, all three types of control samples showed no healing and were unable to carry any load upon reloading. A set of four independently prepared self-healing composite samples showed an average healing efficiency of 60%. When the healing efficiency is calculated relative to the critical load for the virgin, neat resin control (upper horizontal line in Fig. 2), a value slightly greater than 100% is achieved. The average critical load for virgin self-healing samples containing capsules and Grubbs' catalyst was 20% larger than the average value for the neat epoxy control samples, indicating that the addition of capsules and catalyst increases the inherent toughness of the epoxy.

Obviously, numerous modifications and variations of the present invention are possible in light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described herein.

CLAIMS

1. A composite material, comprising:
(i) a polymer,
(ii) a polymerizer,
5 (iii) a corresponding catalyst for the polymerizer, and
(iv) a plurality of capsules,
wherein the polymerizer is in the capsules.
2. The composite material of claim 1, wherein the polymerizer
comprises at least one monomer selected from the group consisting of cyclic
10 olefins, lactones, lactams, acrylates, acrylic acids, alkyl acrylates, alkyl acrylic
acids, styrenes, isoprene and butadiene.
3. The composite material of claim 1, wherein the polymerizer
comprises cyclic olefins.
4. The composite material of claim 1, wherein the polymer
15 comprises at least one member selected from the group consisting of
polyamides, polyesters, polycarbonates, polyethers, polyimides, phenol-
formaldehyde resins, amine-formaldehyde resins, polysulfones,
poly(acrylonitrile-butadiene-styrene), polyurethanes, polyolefins, and
polysilanes.
5. The composite material of claim 1, wherein the polymer
20 comprises at least one member selected from the group consisting of
polyesters and polyethers.
6. The composite material of claim 1, wherein the corresponding
catalyst for the polymerizer comprises at least one monomer selected from
25 the group consisting of ROMP catalysts and cyclic ester polymerization
catalysts.

-13-

7. The composite material of claim 1, wherein the corresponding catalyst for the polymerizer comprises a ROMP catalyst.

8. The composite material of claim 1, wherein the capsules have an aspect ratio of 1:1 to 1:2, and an average diameter of 10 nm to 1 mm.

5 9. The composite material of claim 1, wherein the capsules comprise a polymer of urea and formaldehyde, gelatin, polyurea, and polyamide.

10 10. The composite material of claim 1, wherein
the polymerizer comprises DCPD,
the polymer comprises epoxy,
the corresponding catalyst for the polymerizer comprises a Grubbs catalyst,
the capsules have an aspect ratio of 1:1 to 1:1.5, and an
average diameter of 30-300 μm , and
15 the capsules comprise a polymer of urea and formaldehyde.

20 11. The composite material of claim 1, wherein
the polymerizer comprises DCPD,
the polymer comprises poly(DCPD),
the corresponding catalyst for the polymerizer comprises a Grubbs catalyst, and
the capsules have an aspect ratio of 1:1 to 1:1.5, and an
average diameter of 30-300 μm .

25 12. The composite material of claim 1, wherein
the polymerizer comprises caprolactone,
the polymer comprises poly(caprolactone),
the corresponding catalyst for the polymerizer comprises a scandium triflate, and
the capsules have an aspect ratio of 1:1 to 1:1.5, and an
average diameter of 30-300 μm .

-14-

- 5 13. A composite material, comprising:
 (i) a polymer,
 (ii) a polymerizer,
 (iii) a corresponding activator for the polymerizer, and
 (iv) a first plurality of capsules,
 wherein the polymerizer is in the capsules, and
 the corresponding activator is not a native activating moiety.
- 14 The composite material of claim 13, wherein said corresponding
 activator is a corresponding initiator for the first polymerizer.
- 10 15. The composite material of claim 13, further comprising a second
 plurality of capsules, wherein said activator is in the second plurality of
 capsules.
16. The composite material of claim 14, wherein said corresponding
 activator is a monomer.
- 15 17. The composite material of claim 13, wherein
 said polymerizer comprises a monomer and a first part of a two-
 part catalyst, and
 said corresponding activator is a second part of the two-part
 catalyst.
- 20 18. The composite material of claim 13, wherein the polymer
 comprises at least one member selected from the group consisting of
 polyamides, polyesters, polycarbonates, polyethers, polyimides, phenol-
 formaldehyde resins, amine-formaldehyde resins, polysulfones,
 poly(acrylonitrile-butadiene-styrene), polyurethanes, polyolefins, and
25 polysilanes.
19. The composite material of claim 13, wherein the polymer
 comprises at least one member selected from the group consisting of
 polyesters and polyethers.

-15-

20. The composite material of claim 13, wherein the capsules have an aspect ratio of 1:1 to 1:2, and an average diameter of 10 nm to 1 mm.

21. The composite material of claim 13, wherein the capsules comprise a polymer of urea and formaldehyde, gelatin, polyurea, and polyamide.

22. A method for making the composite of claim 1, comprising: dispersing the capsules and the corresponding catalyst into the polymer.

23. A method for making the composite of claim 13, comprising: dispersing the capsules and the corresponding activator into the polymer.

Figure 1





Figure 2



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 August 2002 (22.08.2002)

PCT

(10) International Publication Number
WO 02/064653 A3

(51) International Patent Classification⁷: C08F 291/00,
C08L 51/08, 51/00, C08G 61/08, C08L 65/00

(21) International Application Number: PCT/US02/04163

(22) International Filing Date: 12 February 2002 (12.02.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/782,609 13 February 2001 (13.02.2001) US

(71) Applicant: BOARD OF TRUSTEES OF UNIVERSITY
OF ILLINOIS [US/US]; 352 Henry Administration Build-
ing, 506 S. Wright, Urbana, IL 61801 (US).

(72) Inventors: WHITE, Scott, R.; 2510 Southwood Drive,
Champaign, IL 61821 (US). SOTTOS, Nancy, R.;
1410 Manchester Drive, Champaign, IL 61822 (US).
GEUBELLE, Philippe, H.; 2102 Crossgate Court, Cham-
paign, IL 61822 (US). MOORE, Jeffery, S.; 807 Vista
Drive, Savoy, IL 61874 (US). SRIRAM, Suresh, R.; 508
E. Michigan Avenue, Apt. 15, Urbana, IL 61801 (US).
KESSLER, Michael, R.; 1303 W. Beardley Avenue,
Urbana, IL 61801 (US). BROWN, Eric, N.; 621 South
Crescent Drive, Apartment 20, Champaign, IL 61821
(US).

(74) Agent: TAYLOR, Jonathan, P.; Brinks Hofer Gilson &
Lione, P.O. Box 10087, Chicago, IL 60610 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN,
YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
12 December 2002

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

WO 02/064653 A3

(54) Title: MULTIFUNCTIONAL AUTONOMICALLY HEALING COMPOSITE MATERIAL

(57) Abstract: A composite material, contains a polymer, a polymerizer, a corresponding catalyst for the polymerizer, and a plurality of capsules. The polymerizer is in the capsules. The composite material is self-healing.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/04163

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F291/00 C08L51/08 C08L51/00 C08G61/08 C08L65/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F C08L C08G C09J C08K G03G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 55753 A (DOW CHEMICAL CO) 4 November 1999 (1999-11-04)	1,4,5,8, 9
Y	* abstract ;page 4, line 21-page 5, line 30, particularly page 5, line 3, 19-20 ;page 5, line 32-page 9, line 22 ;page 12, line 29-page 13, line 6 ;page 16, line 1-10;page 11, line 28-35 ;page 3, line 4-22* page 12, line 9-19; claim 6	2,3,6,7
X	WO 97 25360 A (DOW CHEMICAL CO ;ESSEX SPECIALTY PROD (US)) 17 July 1997 (1997-07-17)	1,4,5,8, 9
Y	page 12, line 13 -page 14, line 30; claims 5-10	2,3,6,7
	--- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

7 June 2002

Date of mailing of the international search report

04.10.2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hammond, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US-02/04163

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 801 033 A (HOSSAINY SYED F A ET AL) 1 September 1998 (1998-09-01) * column 7, line 51-67, 20-49 ; column 10, line 32-55, particularly "polysaccharides" ; column 8, line 1 - column 9, line 55 ; column 11, line 16-50 * claims 1-21	1
P,X	US 6 258 870 B1 (HOSSAINY SYED F A ET AL) 10 July 2001 (2001-07-10) column 7, line 45-61 ; column 10, line 40-51, particularly "polysaccharides" ; column 11, line 13-47 * the whole document	1
Y	US 6 001 909 A (SETIABUDI FRANS) 14 December 1999 (1999-12-14) * column 19, line 23-25 ; column 18, line 41 - column 19, line 22 ; claims 1-18 * abstract	2,3,6,7
Y	US 5 324 616 A (SACRIPANTE GUERINO G ET AL) -28 June 1994 (1994-06-28) * column 6, line 60 - column 8, line 40 ; examples 1-7 * abstract; claims 1-19	2,3,6,7
A	US 3 069 370 A (JENSEN ERIK H ET AL) 18 December 1962 (1962-12-18) * column 4, line 21-30 ; column 3, line 12 - column 4, line 4 * claims 1-26	1-12
A	WO 99 55794 A (DOW CHEMICAL CO ;ESSEX SPECIALTY PROD (US)) 4 November 1999 (1999-11-04) abstract; claims 1-10	1-12
A	US 4 080 238 A (WOLINSKI LEON E ET AL) 21 March 1978 (1978-03-21) the whole document	1-12
A	US 3 041 289 A (BERNARD KATCHEN ET AL) 26 June 1962 (1962-06-26) the whole document	1-12
A	DE 42 09 031 A (BASF AG) 23 September 1993 (1993-09-23) abstract; claims 1-6	1-12
A	EP 0 349 855 A (TEIJIN LTD) 10 January 1990 (1990-01-10) abstract; claims 1-12	1-12
	-/--	

INTERNATIONAL SEARCH REPORT

International Application No

~~PCT/US 02/04163~~

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 669 368 A (REHAU AG & CO) 30 August 1995 (1995-08-30) abstract; claims 1-19 ---	1-12
A	US 4 755 588 A (VALLANCE MICHAEL A ET AL) 5 July 1988 (1988-07-05) abstract; claims 1-11 -----	1-12

INTERNATIONAL SEARCH REPORT

national application No.
PCT/US-02/.....

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:-

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-12

Remark on Protest

☐ The additional search fees were accompanied by the applicant's protest.

☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-12

A composite material, comprising: (i) a polymer ; (ii) a polymeriser ; (iii) a corresponding catalyst for the polymeriser ; (iv) a plurality of capsules ; wherein the polymeriser is in capsules.

--

2. Claims: 13-21

A composite material, comprising: (i) a polymer ; (ii) a polymeriser ; (iii) a corresponding activator for the polymeriser, wherein the corresponding activator is not a native activating moiety as defined ; (iv) a first plurality of capsules ; wherein the polymeriser is in capsules.

3. Claim : 22

A method for making the composite of claim 1, comprising: dispersing the capsules and the corresponding catalyst into the polymer.

4. Claim : 23

A method for making the composite of claim 13, comprising: dispersing the capsules and the corresponding activator into the polymer.

INTERNATIONAL SEARCH REPORT
Information on patent family members

International Application No
PCT/US 02/04163

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9955753	A	04-11-1999	AU 3966999 A WO 9955753 A1	16-11-1999 04-11-1999
WO 9725360	A	17-07-1997	US 5922809 A AU 724913 B2 AU 1356297 A BR 9612478 A CA 2242333 A1 CN 1209145 A EP 0873369 A1 JP 2000515173 T WO 9725360 A1 US 6133398 A US 5976305 A	13-07-1999 05-10-2000 01-08-1997 13-07-1999 17-07-1997 24-02-1999 28-10-1998 14-11-2000 17-07-1997 17-10-2000 02-11-1999
US 5801033	A	01-09-1998	US 5529914 A AU 683209 B2 AU 3780993 A BR 9306041 A CA 2117584 A1 EP 0627912 A1 JP 3011767 B2 JP 7506961 T NZ 251039 A US 5573934 A WO 9316687 A1 US 5858746 A US 5834274 A US 5843743 A US 6258870 B1 US 2002058318 A1 AT 197125 T AU 673160 B2 AU 3735393 A BR 9306038 A CA 2117588 A1 DE 69329594 D1 DE 69329594 T2 DK 627911 T3 EP 0627911 A1 ES 2153378 T3 JP 3011768 B2 JP 7507056 T KR 266912 B1 NZ 249770 A PT 627911 T US 2002091229 A1 US 5410016 A WO 9317669 A1 US 6060582 A US 5468505 A US 5626863 A US 5567435 A US 6306922 B1 US 5986043 A	25-06-1996 06-11-1997 13-09-1993 18-11-1997 02-09-1993 14-12-1994 21-02-2000 03-08-1995 26-03-1996 12-11-1996 02-09-1993 12-01-1999 10-11-1998 01-12-1998 10-07-2001 16-05-2002 15-11-2000 31-10-1996 05-10-1993 13-01-1998 16-09-1993 30-11-2000 31-05-2001 20-11-2000 14-12-1994 01-03-2001 21-02-2000 03-08-1995 01-12-2000 25-09-1996 30-04-2001 11-07-2002 25-04-1995 16-09-1993 09-05-2000 21-11-1995 06-05-1997 22-10-1996 23-10-2001 16-11-1999
US 6258870	B1	10-07-2001	US 5529914 A US 2002058318 A1	25-06-1996 16-05-2002

INTERNATIONAL SEARCH REPORT
information on patent family members

International Application No

PCT/US 02/04163

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6258870	B1	AU 683209 B2	06-11-1997
		AU 3780993 A	13-09-1993
		BR 9306041 A	18-11-1997
		CA 2117584 A1	02-09-1993
		EP 0627912 A1	14-12-1994
		JP 3011767 B2	21-02-2000
		JP 7506961 T	03-08-1995
		NZ 251039 A	26-03-1996
		US 5573934 A	12-11-1996
		WO 9316687 A1	02-09-1993
		US 5858746 A	12-01-1999
		US 5834274 A	10-11-1998
		US 5843743 A	01-12-1998
		US 5801033 A	01-09-1998
		AT 197125 T	15-11-2000
		AU 673160 B2	31-10-1996
		AU 3735393 A	05-10-1993
		BR 9306038 A	13-01-1998
		CA 2117588 A1	16-09-1993
		DE 69329594 D1	30-11-2000
		DE 69329594 T2	31-05-2001
		DK 627911 T3	20-11-2000
		EP 0627911 A1	14-12-1994
		ES 2153378 T3	01-03-2001
		JP 3011768 B2	21-02-2000
		JP 7507056 T	03-08-1995
		KR 266912 B1	01-12-2000
		NZ 249770 A	25-09-1996
		PT 627911 T	30-04-2001
		US 2002091229 A1	11-07-2002
		US 5410016 A	25-04-1995
		WO 9317669 A1	16-09-1993
		US 6060582 A	09-05-2000
		US 5468505 A	21-11-1995
		US 5626863 A	06-05-1997
		US 5567435 A	22-10-1996
		US 6306922 B1	23-10-2001
		US 5986043 A	16-11-1999
US 6001909	A	CA 2189311 A1	03-05-1997
		EP 0771830 A2	07-05-1997
		JP 9183833 A	15-07-1997
US 5324616	A	JP 6027714 A	04-02-1994
US 3069370	A	CH 386995 A	31-01-1965
		DE 1233829 B	09-02-1967
		FR 1279235 A	22-12-1961
		GB 929225 A	19-06-1963
WO 9955794	A	AU 3666699 A	16-11-1999
		AU 3666899 A	16-11-1999
		BR 9910037 A	26-12-2000
		BR 9910333 A	09-01-2001
		CA 2329804 A1	04-11-1999
		CA 2330384 A1	04-11-1999
		CN 1298415 T	06-06-2001
		CN 1298433 T	06-06-2001

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/04163

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9955794	A		EP 1076679 A1	21-02-2001
			EP 1080126 A1	07-03-2001
			JP 2002513052 T	08-05-2002
			JP 2002513068 T	08-05-2002
			US 2002100550 A1	01-08-2002
			WO 9955794 A1	04-11-1999
			WO 9955755 A1	04-11-1999
			US 6355127 B1	12-03-2002
			US 2002010272 A1	24-01-2002
US 4080238	A	21-03-1978	JP 53009838 A	28-01-1978
			US 4297158 A	27-10-1981
			US 4200480 A	29-04-1980
			US 4155950 A	22-05-1979
US 3041289	A	26-06-1962	BE 585460 A	
			CH 392469 A	31-05-1965
			DE 1141256 B	20-12-1962
			DE 1191256 B	15-04-1965
			FR 1334918 A	16-08-1963
			GB 870476 A	14-06-1961
			NL 125294 C	
			NL 246986 A	
DE 4209031	A	23-09-1993	DE 4209031 A1	23-09-1993
EP 0349855	A	10-01-1990	EP 0349855 A2	10-01-1990
			JP 2276852 A	13-11-1990
			JP 2859300 B2	17-02-1999
			KR 9402280 B1	21-03-1994
			US 5096644 A	17-03-1992
EP 0669368	A	30-08-1995	DE 4405745 A1	07-12-1995
			AT 185826 T	15-11-1999
			EP 0669368 A1	30-08-1995
			ES 2139102 T3	01-02-2000
US 4755588	A	05-07-1988	EP 0257467 A2	02-03-1988
			JP 63108025 A	12-05-1988